

**1305.1904 SECTION 1904, DURABILITY REQUIREMENTS.**

IBC section 1904.3 is amended to read as follows:

**1904.3 Corrosion protection.** Where bonded reinforcing and pre-stressing steel is located in concrete assigned to Exposure Class F3 or Exposure Class C2, the steel shall be protected from corrosion by one of the following methods:

1. impermeable barrier;
2. epoxy coating in accordance with ACI 318; or
3. hot dipped galvanizing in accordance with ACI 318.

**Statutory Authority:** *MS s 326B.02*

**History:** *44 SR 609*

**Published Electronically:** *March 31, 2020*