1309.0402 SECTION R402, MATERIALS.

IRC Table R402.2 is amended to read as follows:

TABLE R402.2 MINIMUM SPECIFIED COMPRESSIVE STRENGTH OF CONCRETE

TYPE OR LOCATION OF CONCRETE CONSTRUCTION	MINIMUM SPECIFIED COMPRESSIVE STRENGTH ^a (f ¹ _c) Weathering Potential ^b		
	Footings ^g	5,000	5,000
Basement walls, foundations, and other concrete not exposed to the weather	2,500	2,500	2,500°
Basement slabs and interior slabs on grade, except garage floor slabs	2,500	2,500	2,500°
Basement walls, foundation walls, exterior walls, and other vertical concrete work exposed to the weather	2,500	3,000 ^d	3,000 ^d
Porches, carport slabs, and steps exposed to the weather, and garage floor slabs	2,500	3,000 ^{d, e, f}	3,500 ^{d, e, f}

For SI: 1 pound per square inch = 6.895 kPa.

- a. Strength at 28 days psi.
- b. See Table R301.2(1) for weathering potential.

- c. Concrete in these locations that may be subject to freezing and thawing during construction shall be air-entrained concrete in accordance with Footnote d.
- d. Concrete shall be air-entrained. Total air content (percent by volume of concrete) shall be not less than 5 percent or more than 7 percent.
- e. See section R402.2 for maximum cementitious materials content.
- f. For garage floors with a steel-troweled finish, reduction of the total air content (percent by volume of concrete) to not less than 3 percent is permitted if the specified compressive strength of the concrete is increased to not less than 4,000 psi.
- g. Compressive strength (f_c^1) of 2,500 psi, with an approved admixture that provides a water and vapor resistance at least equivalent to 5,000 psi concrete.

Statutory Authority: MS s 326B.02; 326B.101; 326B.106

History: 39 SR 91;

Published Electronically: January 26, 2015